



TECHNICAL DATA SHEET

CondenStop® Light

Application: Anti Condensation Drip for use in lower risk environments

Order Code: S25212

Composition

• Fiber	Polyester
• Binder	Acrylate / PAN - PMMA - microspheres
• Finish	Hotmelt adhesive
• Colour	Standard Grey or Bright White
• Release Foil	HDPE-liner

Absorption & Drying Properties

<i>NF P 15-203-1</i>	<i>Unit</i>	<i>Value</i>	<i>Conditions</i>
• Absorption (condensed water)	g/m ² (lbs/100 ft ²)	600 (12)	100%RH, ΔT:17°C (31°F)
• Time to drip	time (hrs)	> 4	100%RH, 40°C (104°F), ΔT:17°C (31°F)
• Drying speed	g/m ² /h (lbs/100 ft ² /h)	80 (1.64)	50%RH, 23°C (73°F)
<i>DIN 53.923</i>			
• Absorption (immersion test)	g/m ² (lbs/100 ft ²)	>600 (>12)	24 hrs full immersion in water

Flame & Thermal Properties

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
• Flame retardancy	Class	I ¹	ASTM 84-04
• Thermal conductivity	(λ) W/mK	0.02	
• R-value	m ² K/W	0.065	
• CondenStop® can be qualified as class I ¹ impervious to mold growth ²			

Mechanical Properties

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
Tensile strength:			
• Machine direction	N/5 cm (lbf/in)	80 (9.1)	ISO 9073-3
• Cross direction	N/5 cm (lbf/in)	10 (1.1)	ISO 9073-3
Elongation:			
• Machine direction	%	20	ISO 9073-3
• Cross direction	%	120	ISO 9073-3

Dimensions & Packaging

	<i>Unit</i>	<i>Value</i>	<i>Standard</i>
• Weight ³	g/m ² (lbs/100 ft ²)	70 (1.4)	ISO 9073-1
• Thickness	mm (mils)	0.9 (35)	ISO 9073-2
• Max. Width	mm (inch)	1520 (60)	
• Core Diameter (ID)	mm (inch)	76 (3)	
• Roll-length	m (foot)	1500 (4500)	
• Packaging	PE Stretch Foil		

Visit us at www.condenstop.com for more information

1 Classification from the Model Building Codes, 2 Testing and classification by TNO Construction, 3 Excluding Release Foil

Reasonable care has been taken in the preparation of this information, but the manufacturer makes no warranty of merchantability or any other warranty, expressed or implied, with respect to this information. The manufacturer makes no representations and assumes no liability for any direct, incidental or consequential damages resulting from its use. Physical property values presented in this document are nominal values obtained by using listed and unlisted methods. Data are subject to normal manufacturing variations and are subject to change without notice. The most recent version of this document supersedes all previous versions. All Rights Reserved. CondenStop and the Stop Sign Logo are registered trademarks of Lantor BV. 2006-08